Solvay Engineered Polymers DEXPRO® R210 TPV - High-Impact Polypropylene (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV) , Polypropylene (PP)

Material Notes:

Description: DEXPRO® R210 is a high-impact polypropylene co-polymer molding compound. Applications: Exterior trimInformation

provided by Solvay Engineered Polymers. LyondellBasell acquired Solvay Engineered Polymers in 2008. This grade is not part of the current

LyondellBasell product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Engineered-Polymers-DEXPRO-R210-TPV-High-Impact-Polypropylene-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|-----------------------|---------------------|---------------------|---------------------|
| Specific Gravity | 0.900 g/cc | 0.900 g/cc | ISO 1183 |
| Linear Mold Shrinkage | 0.013 - 0.016 cm/cm | 0.013 - 0.016 in/in | as molded; ISO 294 |
| | 0.017 - 0.020 cm/cm | 0.017 - 0.020 in/in | after bake; ISO 294 |
| Melt Flow | 12 g/10 min | 12 g/10 min | ISO 1133 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-----------|----------|---|
| Tensile Strength, Yield | 17.5 MPa | 2540 psi | 150x10x4 mm specimen, 50 mm/min; ISO 527-1/527-2 |
| Flexural Modulus | 0.715 GPa | 104 ksi | 80x10x4 mm specimen, 2 mm/min; ISO 178 |

| Thermal Properties | Metric | English | Comments |
|--------------------|---------------------------------|--------------------------------|-----------|
| CTE, linear | 105 μm/m-°C | 58.3 µin/in-°F | ASTM E228 |
| | @Temperature -30.0 - 80.0 °C | @Temperature -22.0 - 176 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China