

**Solvay SIPOMERÂ® SEM 25 Polyalkoxyl Polyarylphenol Ethylenic Methacrylate**

Category : Fluid

**Material Notes:**Description: Specialty monomer for Rheology modification  
Chemical Name: POLYALKOXYL POLYARYLPHENOL ETHYLENICMETHACRYLATE  
CAS: 79-41-4  
Available in: Asia Pacific, Europe, Latin America and North America  
Applications: SIPOMERÂ© SEM 25 is a unique monomer for use in alkali soluble associative thickness.  
Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-SIPOMER-SEM-25-Polyalkoxyl-Polyarylphenol-Ethylenic-Methacrylate.php](http://www.lookpolymers.com/polymer_Solvay-SIPOMER-SEM-25-Polyalkoxyl-Polyarylphenol-Ethylenic-Methacrylate.php)

Physical Properties	Metric	English	Comments
Density	>= 1.00 g/cc	>= 0.0361 lb/inÂ³	
Solids Content	58 - 62 %	58 - 62 %	
pH	4.5	4.5	
Viscosity	180 cP	180 cP	

Thermal Properties	Metric	English	Comments
Melting Point	<= -30.0 Â°C	<= -22.0 Â°F	Freezing Point
Flash Point	>= 98.0 Â°C	>= 208 Â°F	

Processing Properties	Metric	English	Comments
Moisture Content	18 - 22 %	18 - 22 %	Karl fisher; RP-0327
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Appearance	Clean, Clear Liquid	RP-0064
Composition	Acidity (as Methacrylic, 86)	18-22%, RP-0008
	MEHQ	1000-1200 ppm, RP-0301

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China