

Solvay STANNINE® 5525 Surfactant

Category : Fluid , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Description: Blend of substituted thiourea and surfactants
 Identification: ACID PICKLING INHIBITOR (SUBSTITUTED THIOUREA)
 CAS: 61791-00-2
 Solubility: Complete in acids
 Available in: Asia Pacific, Europe, Latin America and North America
 Applications: Metal decapement and cleaning in acid solution. Acid pickling inhibitor. Efficient for all types of acids (sulfuric, phosphoric, sulfonic, citric, acetic, glycollic) and for hydrochloric acid up to 50°C.
 Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-STANNINE-5525-Surfactant.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------------------------|----------|
| Density | 1.04 - 1.06 g/cc | 0.0376 - 0.0383 lb/in ³ | AN4037 |

| Thermal Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Flash Point | 170 °C | 338 °F | |

| Optical Properties | Metric | English | Comments |
|----------------------|---------------|---------------|----------|
| Refractive Index | 1.488 - 1.494 | 1.488 - 1.494 | AN4040 |
| Gardner Color Number | <= 10 | <= 10 | AN3013 |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life | 24.0 Month | 24.0 Month | |

| Descriptive Properties | Value | Comments |
|------------------------|------------------|----------------|
| Appearance | Greasy liquid | |
| Cloud Point | 12°C | |
| Composition | Dibutyl-thiouree | 23-25%, AN7011 |
| Setting point | -5°C | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China