

Solvay Specialty Polymers FOMBLIN® Y H-VAC 18/8 PFPE Pump Oil

Category : Fluid , Lubricant , Perfluoropolyether (PFPE)

Material Notes:

FOMBLIN Y fluids are a mixture of fluorinated polymers obtained by a photochemical process that begins with hexafluoropropylene. Since the FOMBLIN chemical chain contains only carbon, fluorine, and oxygen atoms, the PFPEs have exceptional properties such as: low vapor pressure; chemical inertness; non-flammability; high thermal stability; no flash or fire point; low toxicity; excellent compatibility with metals, plastics, elastomers; low volatility; good aqueous and non-aqueous solvent resistance; high dielectric properties; low surface tension; good radiation stability; and environmentally friendly-do not damage the ozone. Information provided by Solvay Solexis, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-FOMBLIN-Y-H-VAC-188-PFPE-Pump-Oil.php

Physical Properties	Metric	English	Comments
Density	1.89 g/cc	0.0683 lb/in ³	ASTM D891
Kinematic Viscosity	190 cSt @Temperature 20.0 °C	190 cSt @Temperature 68.0 °F	ASTM D445
Molecular Weight	2800 g/mol	2800 g/mol	
Vapor Pressure	2.67e-11 bar @Temperature 20.0 °C	2.00e-8 torr @Temperature 68.0 °F	Knudsen
	2.67e-7 bar @Temperature 100 °C	0.000200 torr @Temperature 212 °F	Knudsen

Thermal Properties	Metric	English	Comments
Heat of Vaporization	37.7 J/g @Temperature 200 °C	16.2 BTU/lb @Temperature 392 °F	
Pour Point	-42.0 °C	-43.6 °F	ASTM D97

Optical Properties	Metric	English	Comments
Refractive Index	1.299	1.299	n ₀ >20</sup>

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China