

## Solvay Specialty Polymers Halar® 300 ECTFE Fluoropolymer (discontinued \*\*)

Category : Polymer , Thermoplastic , Fluoropolymer , ETFE/ECTFE , ECTFE Fluoropolymer

### Material Notes:

Data provided by the manufacturer. HALAR® Fluoropolymers have excellent barrier properties, high resistance to a variety of corrosive chemicals and solvents, low flammability, and ease of processing.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-Specialty-Polymers-Halar-300-ECTFE-Fluoropolymer-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Halar-300-ECTFE-Fluoropolymer-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.68 g/cc	0.0607 lb/in <sup>3</sup>	
Water Absorption	<= 0.10 %	<= 0.10 %	168 hours
Moisture Absorption at Equilibrium	<= 0.10 %	<= 0.10 %	after 168 hours

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	
Hardness, Shore D	75	75	
Tensile Strength, Ultimate	54.0 MPa	7830 psi	
Tensile Strength, Yield	30.0 MPa	4350 psi	
Elongation at Break	250 %	250 %	
Elongation at Yield	5.0 %	5.0 %	
Tensile Modulus	1.655 GPa	240.0 ksi	
Flexural Yield Strength	47.0 MPa	6820 psi	
Flexural Modulus	1.69 GPa	245 ksi	
Izod Impact, Notched	1.22 J/cm	2.29 ft-lb/in	
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Impact Strength	806 kJ/m <sup>2</sup>	384 ft-lb/in <sup>2</sup>	ASTM D1822S
Coefficient of Friction, Dynamic	0.19	0.19	vs. steel; 50 cm/s (20 in/s); ASTM D1044
Coefficient of Friction, Static	0.19	0.19	vs. steel; ASTM D1044
Taber Abrasion, mg/1000 Cycles			CS-17 wheels; 500 g; wheels cleaned

Mechanical Properties	5.0 Metric	5.0 English	every 25 cycles Comments
<b>Thermal Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
CTE, linear	80.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature -30.0 - 50.0 $^{\circ}\text{C}$	@Temperature -22.0 - 122 $^{\circ}\text{F}$	
	135 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	75.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 85.0 - 125 $^{\circ}\text{C}$	@Temperature 185 - 257 $^{\circ}\text{F}$	
Specific Heat Capacity	0.946 J/g- $^{\circ}\text{C}$	0.226 BTU/lb- $^{\circ}\text{F}$	
Thermal Conductivity	0.151 W/m-K	1.05 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	
Melting Point	240 $^{\circ}\text{C}$	464 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	150 $^{\circ}\text{C}$	302 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	90.0 $^{\circ}\text{C}$	194 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	63.0 $^{\circ}\text{C}$	145 $^{\circ}\text{F}$	
Brittleness Temperature	$\leq -76.0$ $^{\circ}\text{C}$	$\leq -105$ $^{\circ}\text{F}$	
Flammability, UL94	V-0	V-0	
	@Thickness 0.180 mm	@Thickness 0.00709 in	
Oxygen Index	$\geq 52$ %	$\geq 52$ %	

Optical Properties	Metric	English	Comments
Refractive Index	1.4476	1.4476	Halar® 500
	@Wavelength 589 nm	@Wavelength 589 nm	
Haze	3.0 - 5.0 %	3.0 - 5.0 %	typical for HALAR films; ASTM D1003
Gloss	85 - 95 %	85 - 95 %	85-95% at 20° is typical of HALAR films; ASTM D2457

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.56e+16 ohm-cm	1.56e+16 ohm-cm	
Surface Resistance	$\geq 1.00\text{e}+17$ ohm	$\geq 1.00\text{e}+17$ ohm	ASTM D257
Dielectric Constant	2.5	2.5	
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Electrical Properties	Metric	English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	14.0 kV/mm	356 kV/in	
	@Thickness 3.18 mm	@Thickness 0.125 in	
	21.0 kV/mm	533 kV/in	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	80.0 kV/mm	2030 kV/in	
	@Thickness 0.0250 mm	@Thickness 0.000984 in	
Dissipation Factor	0.0016	0.0016	
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.014	0.014	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	>= 50 sec	>= 50 sec	Test Terminated at 50 sec.; ASTM D495
Comparative Tracking Index	>= 600 V	>= 600 V	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Hot Wire Ignition, HWI	20.2 sec	20.2 sec	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
High Amp Arc Ignition, HAI	>= 200 arcs	>= 200 arcs	test terminated at 200 arcs 1/16 A.S.
	@Thickness 1.60 mm	@Thickness 0.0630 in	
High Voltage Arc-Tracking Rate, HVTR	208 mm/min	8.19 in/min	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Processing Temperature	260 - 282 °C	500 - 540 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China