

Solvay Specialty Polymers Hylar® MP10 PVDF Polyvinylidene Fluoride (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

Material Notes:

Data provided by the manufacturer. Hylar® polymers have the characteristic stability of fluoropolymers combined with a unique polarity that influences its solubility and electrical properties. In addition to standard molding and extrusion, Hylar® polymers lend themselves well to solution-applied coatings.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Hylar-MP10-PVDF-Polyvinylidene-Fluoride-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.77 - 1.79 g/cc	0.0639 - 0.0647 lb/in ³	ASTM D792
Water Absorption	0.020 %	0.020 %	ASTM D570
Linear Mold Shrinkage	0.025 - 0.030 cm/cm	0.025 - 0.030 in/in	
Melt Flow	8.0 - 10 g/10 min @Load 3.80 kg	8.0 - 10 g/10 min @Load 8.38 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	76 - 80	76 - 80	ASTM D2240
Tensile Strength, Ultimate	35.0 - 45.0 MPa	5080 - 6530 psi	ASTM D638
Tensile Strength, Yield	34.0 - 48.0 MPa	4930 - 6960 psi	ASTM D638
Elongation at Break	50 - 250 %	50 - 250 %	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Tensile Modulus	1.70 - 3.10 GPa	247 - 450 ksi	ASTM D638
Flexural Yield Strength	55.0 - 76.0 MPa	7980 - 11000 psi	ASTM D790
Flexural Modulus	1.73 - 2.41 GPa	251 - 350 ksi	ASTM D790
Izod Impact, Notched	0.800 - 1.30 J/cm	1.50 - 2.44 ft-lb/in	
Izod Impact, Unnotched	>= 15.0 J/cm	>= 28.1 ft-lb/in	Low Temp; ASTM D256
Coefficient of Friction, Dynamic	0.12 - 0.15	0.12 - 0.15	ASTM D1894
Coefficient of Friction, Static	0.10 - 0.15	0.10 - 0.15	ASTM D1894

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear	100 - 120 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	55.6 - 66.7 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM D696
	@Temperature 20.0 $^\circ\text{C}$	@Temperature 68.0 $^\circ\text{F}$	
Specific Heat Capacity	1.50 J/g- $^\circ\text{C}$	0.359 BTU/lb- $^\circ\text{F}$	DSC
Thermal Conductivity	0.190 - 0.220 W/m-K	1.32 - 1.53 BTU-in/hr-ft ² - $^\circ\text{F}$	ASTM C177
Melting Point	165 - 168 $^\circ\text{C}$	329 - 334 $^\circ\text{F}$	ASTM D3418
Maximum Service Temperature, Air	150 $^\circ\text{C}$	302 $^\circ\text{F}$	No oxidative or thermal degradation after 5 years at 150 $^\circ\text{C}$ (300 $^\circ\text{F}$)
Deflection Temperature at 1.8 MPa (264 psi)	105 - 115 $^\circ\text{C}$	221 - 239 $^\circ\text{F}$	TMA
Brittleness Temperature	\leq -30.0 $^\circ\text{C}$	\leq -22.0 $^\circ\text{F}$	ASTM D2236
Flammability, UL94	V-0	V-0	
Oxygen Index	44 %	44 %	ASTM D2863

Optical Properties	Metric	English	Comments
Refractive Index	1.42	1.42	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.25e+15 ohm-cm	1.25e+15 ohm-cm	ASTM D257
Dielectric Constant	5.6	5.6	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	6.9	6.9	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Dissipation Factor	13.0 kV/mm	330 kV/in	Short-Time 500 V/sec
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.035	0.035	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Arc Resistance	0.158	0.158	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	\geq 50 sec	\geq 50 sec	ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	215 - 232 $^\circ\text{C}$	419 - 450 $^\circ\text{F}$	Preheat

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China