

Solvay Specialty Polymers KetaSpire® KT-820P Polyetheretherketone (PEEK) (Unverified Data**)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

Material Notes:

KetaSpire KT-820P is a low flow grade of unreinforced polyetheretherketone (PEEK) supplied in a natural-color coarse powder form. KetaSpire PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids, and bases. These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing, and other industrial uses. KetaSpire KT-820P is intended for extrusion compounding. This powder is also available as KT-820NT in a natural-color pellet form for injection molding. Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-KetaSpire-KT-820P-Polyetheretherketone-PEEK-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength	96.0 MPa	13900 psi	ASTM D638
Elongation at Break	20 - 30 %	20 - 30 %	Crystallized; ASTM D638
	>= 60 %	>= 60 %	
Elongation at Yield	5.2 %	5.2 %	ASTM D638
Tensile Modulus	3.60 GPa	522 ksi	ASTM D638
Flexural Strength	152 MPa	22000 psi	ASTM D790
Flexural Modulus	3.90 GPa	566 ksi	ASTM D790
Izod Impact, Notched	0.700 J/cm	1.31 ft-lb/in	ASTM D256
	NB	NB	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	43.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	23.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	TMA; ASTM E831
	@Temperature -50.0 - 50.0 $^\circ\text{C}$	@Temperature -58.0 - 122 $^\circ\text{F}$	

Melting Point Thermal Properties	340 °C Metric	644 °F English	ASTM D3417 Comments
Deflection Temperature at 1.8 MPa (264 psi)	162 °C	324 °F	Unannealed; ASTM D648
Glass Transition Temp, Tg	150 °C	302 °F	ASTM D3417

Descriptive Properties	Value	Comments
Appearance	Natural Color	
Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Features	Ductile	
	Fatigue Resistant	
	Flame Retardant	
	Good Chemical Resistance	
	Good Dimensional Stability	
	Good Impact Resistance	
	High Heat Resistance	
Forms	Powder	
Generic	PEEK	
Processing Method	Compression Molding	
RoHS Compliance	RoHS Compliant	
Uses	Electrical/Electronic Applications	
	Industrial Applications	
	Semiconductor Molding Compounds	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China