

Solvay Specialty Polymers Ryton® QC160P Polyphenylene Sulfide (PPS)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), Unreinforced, Extruded

Material Notes:

Ryton® QC160P (pelletized) polyphenylene sulfide exhibits excellent thermal stability and chemical resistance and is suitable for thermoplastic extrusion processes. Features: Good Chemical Resistance; Good Thermal Stability Additional Properties: Ash Content - ISO 3451-1 0.3 wt%; Volatiles - (150°C): < 0.3 wt% Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Ryton-QC160P-Polyphenylene-Sulfide-PPS.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ASTM D792
Water Absorption	0.050 % @Time 86400 sec	0.050 % @Time 24.0 hour	ISO 62
Melt Flow	45 g/10 min @Load 5.00 kg, Temperature 316 °C	45 g/10 min @Load 11.0 lb, Temperature 601 °F	Procedure B; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Stress	75.0 MPa	10900 psi	ISO 527-2
Elongation at Break	6.0 %	6.0 %	ISO 527-2
Tensile Modulus	3.40 GPa	493 ksi	ISO 527-2
Flexural Strength	130 MPa	18900 psi	ISO 178
Flexural Modulus	3.40 GPa	493 ksi	ISO 178
Izod Impact, Notched	0.530 J/cm @Thickness 3.18 mm	0.993 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	Notch A; ISO 180

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 µm/m-°C @Temperature -50.0 - 50.0 °C	27.8 µin/in-°F @Temperature -58.0 - 122 °F	2
	120 µm/m-°C @Temperature 100 - 200 °C	66.7 µin/in-°F @Temperature 212 - 392 °F	2

Thermal Properties	Metric	English	Comments
Melting Point	280 Â°C	536 Â°F	ISO 11357-3
Deflection Temperature at 0.46 MPa (66 psi)	160 Â°C	320 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	95.0 Â°C	203 Â°F	Unannealed; ASTM D648
Vicat Softening Point	>= 180 Â°C	>= 356 Â°F	ISO 306
Glass Transition Temp, Tg	90.0 Â°C	194 Â°F	ISO 11357-2
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
Oxygen Index	44 %	44 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257
Dielectric Constant	3.2 @Frequency 1.00e+6 Hz	3.2 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	24.0 kV/mm	610 kV/in	ASTM D149
Dissipation Factor	0.0020 @Frequency 1.00e+6 Hz	0.0020 @Frequency 1.00e+6 Hz	ASTM D150

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	Latin America	
	North America	
Color	Natural	
Form	Pellets	
Processing Technique	Extrusion	
RoHS Compliance	RoHS Compliant	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China