

Solvay Specialty Polymers Solef® 31508 Polyvinylidene Fluoride (PVDF)

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

Material Notes:

Solef® 31508 PVDF copolymer is a low viscosity and very flexible grade for Wire & Cable applications. Features: Copolymer; Good Flexibility; Low Viscosity Uses: Wire & Cable Applications Additional Properties: Crystallization Heat - ASTM D3417 22.0 to 28.0 J/g; Heat of Fusion - ASTM D3417 23.0 to 29.0 J/g Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Solef-31508-Polyvinylidene-Fluoride-PVDF.php

Physical Properties	Metric	English	Comments
Density	1.75 - 1.80 g/cc	0.0632 - 0.0650 lb/in ³	ASTM D792
Water Absorption	<= 0.040 % @Time 86400 sec	<= 0.040 % @Time 24.0 hour	ISO 62
Linear Mold Shrinkage, Flow	0.020 - 0.030 cm/cm	0.020 - 0.030 in/in	
Melt Flow	3.0 - 8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 - 8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	53	53	ASTM D2240
Tensile Strength at Break	14.0 - 30.0 MPa @Thickness 2.00 mm	2030 - 4350 psi @Thickness 0.0787 in	50 mm/min; ASTM D638
Tensile Strength, Yield	14.0 - 35.0 MPa @Thickness 2.00 mm	2030 - 5080 psi @Thickness 0.0787 in	50 mm/min; ASTM D638
Elongation at Break	350 - 600 %	350 - 600 %	50 mm/min; ASTM D638
Elongation at Yield	10 - 12 %	10 - 12 %	50 mm/min; ASTM D638
Tensile Modulus	0.400 - 0.600 GPa	58.0 - 87.0 ksi	1.0 mm/min; ASTM D638
Izod Impact, Notched	10.0 J/cm @Thickness 4.00 mm	18.7 ft-lb/in @Thickness 0.157 in	ASTM D256
Coefficient of Friction	0.20 - 0.40	0.20 - 0.40	vs. Itself; ASTM D1894
Coefficient of Friction, Dynamic	0.20 - 0.30	0.20 - 0.30	vs. Itself; ASTM D1894
Taber Abrasion, mg/1000 Cycles	5.0 - 10	5.0 - 10	CS-10 Wheel, 1000 g; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	130 - 150 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	72.2 - 83.3 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	1
	@Temperature 0.000 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature 32.0 - 104 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	1.20 J/g- $\text{Å}^\circ\text{C}$	0.287 BTU/lb- $\text{Å}^\circ\text{F}$	ASTM C351
	@Temperature 23.0 $\text{Å}^\circ\text{C}$	@Temperature 73.4 $\text{Å}^\circ\text{F}$	
	1.60 J/g- $\text{Å}^\circ\text{C}$	0.382 BTU/lb- $\text{Å}^\circ\text{F}$	ASTM C351
	@Temperature 100 $\text{Å}^\circ\text{C}$	@Temperature 212 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	ASTM C177
	@Temperature 23.0 $\text{Å}^\circ\text{C}$	@Temperature 73.4 $\text{Å}^\circ\text{F}$	
Melting Point	167 - 171 $\text{Å}^\circ\text{C}$	333 - 340 $\text{Å}^\circ\text{F}$	DSC
Crystallization Temperature	125 - 131 $\text{Å}^\circ\text{C}$	257 - 268 $\text{Å}^\circ\text{F}$	Peak; ASTM D3418
Vicat Softening Point	110 $\text{Å}^\circ\text{C}$	230 $\text{Å}^\circ\text{F}$	Rate A (50 $\text{Å}^\circ\text{C}/\text{h}$), Loading 2 (50 N)
Glass Transition Temp, Tg	-28.0 $\text{Å}^\circ\text{C}$	-18.4 $\text{Å}^\circ\text{F}$	ASTM E1356
Flammability, UL94	V-0	V-0	
	@Thickness 0.100 mm	@Thickness 0.00394 in	
Oxygen Index	48 %	48 %	ASTM D2863
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+14$ ohm-cm	$\geq 1.00\text{e}+14$ ohm-cm	ASTM D257
Surface Resistance	$\geq 1.00\text{e}+14$ ohm	$\geq 1.00\text{e}+14$ ohm	ASTM D257
Dielectric Constant	7.0	7.0	ASTM D150
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	20.0 - 25.0 kV/mm	508 - 635 kV/in	ASTM D149
	@Thickness 1.00 mm	@Thickness 0.0394 in	

Descriptive Properties	Value	Comments
Availability	Africa & Middle East	
	Asia Pacific	

Descriptive Properties	Europe Value	Comments
	Latin America	
	North America	
Form	Granules	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China