

Solvay Specialty Polymers Veradel[®] 3000RP Polyethersulfone (PESU)

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

Veradel[®] 3000RP hydroxyl-functionalized polyethersulfones (r-PESU) is an amorphous, high-temperature sulfone polymer featuring reactive end groups to enhance solubility for dissolving or dispersing into solutions and to improve adhesion to substrates when used as a coating. Veradel[®] 3000RP r-PESU offers excellent toughness and outstanding hydrolytic resistance. It resists attack from steam, boiling water and mineral acids. Cast films or coatings of r-PESU are transparent and have additional desirable properties, including long term thermal stability, excellent metal adhesion and formability and inherent flame resistance. Features: Acid Resistant; Flame Retardant; Food Contact Acceptable; Good Adhesion; Good Chemical Resistance; Good Creep Resistance; Good Dimensional Stability; Good Thermal Stability; Good Toughness; High Heat Resistance; High Molecular Weight; High Tensile Strength; Hydrolysis Resistant; Low Flow; Medium Rigidity Uses: Adhesives; Cast Film; Coating Applications Additional Properties: Moisture Content - Internal Method 1.5 %; OH End Groups - Internal Method 50 $\mu\text{eq/g}$; Particle Size - Internal Method 250 μm ; Residual Solvent - Internal Method 1.5 % Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Veradel-3000RP-Polyethersulfone-PESU.php

Physical Properties	Metric	English	Comments
Viscosity	700 cP	700 cP	Solution Viscosity; ASTM D455

Mechanical Properties	Metric	English	Comments
Tensile Strength	90.0 MPa	13100 psi	ASTM D638
Elongation at Yield	6.5 %	6.5 %	ASTM D638
Tensile Modulus	2.70 GPa	392 ksi	ASTM D638
Flexural Strength	2.60 MPa	377 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	220 $^{\circ}\text{C}$	428 $^{\circ}\text{F}$	ASTM E1356

Descriptive Properties	Value	Comments
Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Latin America Value	Comments
	North America	
Color	Transparent - Slight Yellow	
Form	Granules; Powder	
Processing Technique	Cast Film; Coating; Solution Processing; Spraying	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China