

Solvay TECHNYL® 1015CR PA6, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Description: Polyamide 6, unfilled, standard for fast injection cycles, for injection molding Available in: Asia Pacific Product Applications: TECHNYL® 1015CR has high fluidity and a good mould release. It is particularly suitable for the production of technical moldings with fast injection cycles. This grade is used for: Fastener, Clip, Gear, Bobbin. This product is available in Natural color. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-TECHNYL-1015CR-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093
Dielectric Strength	18.0 kV/mm	457 kV/in	IEC 60243
Dissipation Factor	0.10	0.10	IEC 60250

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China