

Solvay TECHNYLÂ® A 218 V20 Black 21N PA66, 20% glass fiber, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Description: Polyamide PA66, reinforced with 20% of glass fiber, heat stabilized, for injection molding. Available in: EuropeProduct

Applications: TECHNYL A 218 V20 is used in all sectors of industry, offering an excellent combination between thermal and mechanical properties. This grade is commonly used in the automotive industry for engine components, such as: air ducts and various liquid containers.

This product is available in natural, black and grey. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-TECHNYL-A-218-V20-Black-21N-PA66-20-glass-fiber-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/inÂ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	100 MPa	14500 psi	ISO 527 Type 1A
Elongation at Break	5.0 %	5.0 %	ISO 527 Type 1A
Tensile Modulus	5.30 GPa	769 ksi	ISO 527 Type 1A
Flexural Modulus	4.20 GPa	609 ksi	ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/mÂ²	6.19 ft-lb/inÂ²	ISO 180/1A
Charpy Impact Unnotched	7.90 J/cmÂ²	37.6 ft-lb/inÂ²	ISO 179/1eU
Charpy Impact, Notched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	ISO 179/1eA

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
Dielectric Strength	28.0 kV/mm	711 kV/in	IEC 60243
Dissipation Factor	0.11	0.11	IEC 60250
Comparative Tracking Index	350 V	350 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China