

Solvay TECHNYLÂ® A 218G V30 PA66, 30% glass fiber, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Description: Polyamide PA66, reinforced with 30% of glass fiber, for injection molding specially stabilized to improve its resistance automotive cooling liquids. Available in: Europe and Latin America Product Applications: TECHNYLÂ® A 218 V43 is used in all sectors of industry, offering an excellent combination between thermal and mechanical properties. This grade is commonly used in the automotive industry for engine components. This product is available in black. TECHNYLÂ® A 218G V30 is particularly recommended for the injection molding of parts in permanent contact with cooling liquids in cars, such as: -cooling and heating radiator systems, header tanks, thermostat components, inlet/outlet pipes. This product is available in natural. Information provided by Rhodia, Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-TECHNYL-A-218G-V30-PA66-30-glass-fiber-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/inÂ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	135 MPa	19600 psi	ISO 527 Type 1A
Elongation at Break	4.0 %	4.0 %	ISO 527 Type 1A
Tensile Modulus	7.50 GPa	1090 ksi	ISO 527 Type 1A
Izod Impact, Notched (ISO)	16.0 kJ/mÂ²	7.61 ft-lb/inÂ²	ISO 180/1eA
Charpy Impact Unnotched	9.50 J/cmÂ²	45.2 ft-lb/inÂ²	ISO 179/1eU
Charpy Impact, Notched	1.60 J/cmÂ²	7.61 ft-lb/inÂ²	ISO 179/1eA

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
Dielectric Strength	29.0 kV/mm	737 kV/in	IEC 60243
Dissipation Factor	0.11	0.11	IEC 60250
Comparative Tracking Index	425 V	425 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.20 %	<= 0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China