

Solvay Technyl® C216V25 25% Glass Filled Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Information provided by Rhodia; Rhodia has been acquired by Solvay.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Technyl-C216V25-25-Glass-Filled-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ISO 1183-A
Water Absorption	1.0 %	1.0 %	24 Hr.; ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	162 MPa	23500 psi	ISO 527
Elongation at Break	3.9 %	3.9 %	ISO 527
Tensile Modulus	8.41 GPa	1220 ksi	ISO 527
Flexural Strength	260 MPa	37700 psi	ISO 178
Flexural Modulus	8.27 GPa	1200 ksi	ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m ²	5.23 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	222 Â°C	432 Â°F	ISO 3146-C
Deflection Temperature at 0.46 MPa (66 psi)	215 Â°C	419 Â°F	ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	200 Â°C	392 Â°F	ISO 75-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Feed Temperature	225 - 230 Â°C	437 - 446 Â°F	
Middle Barrel Temperature	230 - 240 Â°C	446 - 464 Â°F	Compression Zone
Front Barrel Temperature	240 - 250 Â°C	464 - 482 Â°F	
Nozzle Temperature	241 - 260 Â°C	465 - 500 Â°F	

Melt Temperature Processing Properties	230 - 260 Å°C Metric	446 - 500 Å°F English	Comments
Mold Temperature	80.0 - 100 Å°C	176 - 212 Å°F	Surface
Drying Temperature	80.0 Å°C	176 Å°F	Dehumidifying Dryer
Dry Time	3 - 4 hour	3 - 4 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	
Back Pressure	0.138 - 0.345 MPa	20.0 - 50.0 psi	
Fill Speed	200 - 600 mm/sec	7.87 - 23.6 in/sec	Peripheral Screw Speed

Descriptive Properties	Value	Comments
Injection Speed (cm ³ /sec)	120 - 170 cm ³ /sec	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China