

## Spartech APET SP4110 Copolyester Sheet

Category : Polymer , Thermoplastic , Polyester, TP

### Material Notes:

Description: Copolyester Sheet Information provided by Spartech.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Spartech-APET-SP4110-Copolyester-Sheet.php](http://www.lookpolymers.com/polymer_Spartech-APET-SP4110-Copolyester-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	106	106	ASTM D2240
Tensile Strength at Break	57.9 MPa	8400 psi	ASTM D882
Tensile Strength, Yield	58.6 MPa	8500 psi	ASTM D882
Elongation at Break	300 %	300 %	ASTM D882
Tensile Modulus	2.21 GPa	320 ksi	ASTM D882
Flexural Yield Strength	84.1 MPa	12200 psi	ASTM D790
Flexural Modulus	2.21 GPa	320 ksi	ASTM D790
Izod Impact, Unnotched	0.497 J/cm	0.930 ft-lb/in	ASTM D256
	0.278 J/cm	0.520 ft-lb/in	ASTM D256
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Falling Dart Impact	678 J	500 ft-lb	73°F; ASTM D1709A
	542 J	400 ft-lb	ASTM D1709A
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	57.6 µm/m-°C	32.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	72.2 °C	162 °F	ASTM E540
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Gloss	90 %	90 %	Gardner; ASTM D2523

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China