

Spartech EP5240 Calcium Carbonate Filled Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Calcium Carbonate (CaCO3) Filler

Material Notes:

Provides the highest level of stiffness and heat resistance of filled olefins. Calcium Carbonate filled grades offer an excellent balance of stiffness and impact resistance. Typical applications include extrusion/thermoformed food containers, and profile extruded and blown molded structural parts. Information provided by Spartech

Order this product through the following link:

http://www.lookpolymers.com/polymer_Spartech-EP5240-Calcium-Carbonate-Filled-Homopolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
	@Temperature 22.8 Å°C	@Temperature 73.0 Å°F	
Filler Content	40 %	40 %	
Linear Mold Shrinkage	0.011 cm/cm	0.011 in/in	0.125inch wall

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.8 MPa	3600 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Modulus	0.241 GPa	35.0 ksi	tangent; ASTM D790
	1.86 GPa	270 ksi	secant; ASTM D790
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	ASTM D256
	@Temperature 22.8 Å°C	@Temperature 73.0 Å°F	
Gardner Impact	4.07 J	3.00 ft-lb	ASTM D5420
	@Temperature -5.56 Å°C	@Temperature 22.0 Å°F	
	27.1 J	20.0 ft-lb	ASTM D5420
	@Temperature 22.8 Å°C	@Temperature 73.0 Å°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 Å°C	240 Å°F	ASTM D648

Deflection Temperature at 1.8 MPa Thermal Properties (104 psi)	60.0 Å°C Metric	140 Å°F English	ASTM D648 Comments
Optical Properties	Metric	English	Comments
Gloss	55 %	55 %	60Å°; ASTM D523

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China