

Spartech PE4130 Reinforced High Density Polyethylene Compound

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Spartech Polycom's filled high molecular weight, high density polyethylenes are specifically designed for blow molding and sheet extrusion /thermoforming of structural parts. These materials offer an excellent balance of stiffness, impact resistance and dimensional stability.

Typical applications for blow molding grades include automotive seat cores, heating ducts, and recreational products such as ice chests. Information provided by Spartech

Order this product through the following link:

http://www.lookpolymers.com/polymer_Spartech-PE4130-Reinforced-High-Density-Polyethylene-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc @Temperature 22.8 Â°C	1.19 g/cc @Temperature 73.0 Â°F	ASTM D792
Filler Content	30 %	30 %	Talc
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	0.125inch wall

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.4 MPa	4700 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Strength	46.9 MPa	6800 psi	Max Load; ASTM D790
Flexural Modulus	1.62 GPa	235 ksi	secant; ASTM D790
	2.14 GPa	310 ksi	tangent; ASTM D790
Izod Impact, Notched	1.60 J/cm @Temperature 22.8 Â°C	3.00 ft-lb/in @Temperature 73.0 Â°F	ASTM D256
Gardner Impact	8.13 J @Temperature -5.56 Â°C	6.00 ft-lb @Temperature 22.0 Â°F	ASTM D5420
	>= 33.9 J @Temperature 22.8 Â°C	>= 25.0 ft-lb @Temperature 73.0 Â°F	ASTM D5420

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties Deflection Temperature at 0.46 MPa (66 psi)	Metric C	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	51.7 Â°C	125 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China