

Spartech PP5110 Talc Filled Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Offers an excellent balance of processing improvement and high levels of stiffness and heat deflection temperature. Information provided by Spartech

Order this product through the following link:

http://www.lookpolymers.com/polymer_Spartech-PP5110-Talc-Filled-Homopolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.960 g/cc @Temperature 22.8 Â°C	0.960 g/cc @Temperature 73.0 Â°F	ASTM D792
Filler Content	10 %	10 %	
Linear Mold Shrinkage	0.018 cm/cm	0.018 in/in	0.125inch wall

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.5 MPa	5000 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Flexural Modulus	1.59 GPa	230 ksi	secant; ASTM D790
	2.07 GPa	300 ksi	tangent; ASTM D790
Izod Impact, Notched	0.347 J/cm @Temperature 22.8 Â°C	0.650 ft-lb/in @Temperature 73.0 Â°F	ASTM D256
Gardner Impact	2.71 J @Temperature 22.8 Â°C	2.00 ft-lb @Temperature 73.0 Â°F	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C	230 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	54.4 Â°C	130 Â°F	ASTM D648

Optical Properties	Metric	English	Comments
Gloss	60 %	60 %	60Â°; ASTM D523

Optical Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China