

## Spartech PP5420 Glass Fiber Reinforced Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

**Material Notes:**

Provides the maximum strength and heat resistance among polypropylene compounds. Physical properties can approach those of more expensive engineering resins. Information provided by Spartech

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Spartech-PP5420-Glass-Fiber-Reinforced-Homopolymer.php](http://www.lookpolymers.com/polymer_Spartech-PP5420-Glass-Fiber-Reinforced-Homopolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc @Temperature 22.8 Â°C	1.05 g/cc @Temperature 73.0 Â°F	ASTM D792
Filler Content	20 %	20 %	
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	0.125inch wall

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Flexural Strength	93.1 MPa	13500 psi	Max Load; ASTM D790
Flexural Modulus	3.65 GPa	530 ksi	secant; ASTM D790
	5.48 GPa	795 ksi	tangent; ASTM D790
Izod Impact, Notched	0.694 J/cm @Temperature 22.8 Â°C	1.30 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	152 Â°C	305 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	138 Â°C	280 Â°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**