

## Spartech Royalite R12 ABS General Purpose Sheet

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Sheet

**Material Notes:**

Description: General Purpose Sheet Information provided by Spartech.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Spartech-Royalite-R12-ABS-General-Purpose-Sheet.php](http://www.lookpolymers.com/polymer_Spartech-Royalite-R12-ABS-General-Purpose-Sheet.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.02 - 1.08 g/cc	1.02 - 1.08 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	96	96	ASTM D785
Tensile Strength, Yield	37.2 MPa	5400 psi	ASTM D638
Flexural Yield Strength	61.4 MPa	8900 psi	ASTM D790
Flexural Modulus	1.93 GPa	280 ksi	ASTM D790
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	73°F; ASTM D256
	0.961 J/cm	1.80 ft-lb/in	ASTM D256
	@Temperature -28.9 °C	@Temperature -20.0 °F	
Impact Test	27.1 J	20.0 ft-lb	Dynatup Instrumented Impact; ASTM D3763
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	75.6 - 101 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	42.0 - 56.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	104 °C	220 °F	ASTM D648

Descriptive Properties	Value	Comments
Flammability	Passes	MVSS (Motor Vehicle Safety Standard) 302

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China