

## Special Metals DURANICKEL® 301 (UNS N03301) Spring Wire

Category : Metal , Nonferrous Metal , Nickel Alloy

### Material Notes:

Tensile strength (ultimate) and elongation values reported here are typical for Spring Wire specifically. Other property values are typical of annealed DURANICKEL® alloy 301 or the alloy in general. Data provided by the manufacturer, Special Metals.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Special-Metals-DURANICKEL-301-UNS-N03301-Spring-Wire.php](http://www.lookpolymers.com/polymer_Special-Metals-DURANICKEL-301-UNS-N03301-Spring-Wire.php)

Physical Properties	Metric	English	Comments
Density	8.19 g/cc	0.296 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1100 - 1380 MPa	160000 - 200000 psi	
Elongation at Break	2.0 - 5.0 %	2.0 - 5.0 %	
Modulus of Elasticity	207 GPa	30000 ksi	Tension
Poissons Ratio	0.31	0.31	
Shear Modulus	76.0 GPa	11000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	13.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.22 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Mean; aged
	@Temperature 21.0 - 100 $\text{Å}^\circ\text{C}$	@Temperature 69.8 - 212 $\text{Å}^\circ\text{F}$	
	14.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.78 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Mean; aged
	@Temperature 21.0 - 300 $\text{Å}^\circ\text{C}$	@Temperature 69.8 - 572 $\text{Å}^\circ\text{F}$	
14.7 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	@Temperature 21.0 - 500 $\text{Å}^\circ\text{C}$	8.17 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Mean; aged
		@Temperature 69.8 - 932 $\text{Å}^\circ\text{F}$	
16.6 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	@Temperature 21.0 - 900 $\text{Å}^\circ\text{C}$	9.22 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Mean; aged
		@Temperature 69.8 - 1650 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.435 J/g- $\text{Å}^\circ\text{C}$	0.104 BTU/lb- $\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 100 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 212 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	23.8 W/m-K	165 BTU-in/hr-ft <sup>2</sup> - $\text{Å}^\circ\text{F}$	Age Hardened

Melting Point Thermal Properties	1400 - 1440 Å°C Metric	2550 - 2620 Å°F English	Comments
Solidus	1400 Å°C	2550 Å°F	
Liquidus	1440 Å°C	2620 Å°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	4.0 - 4.75 %	4.0 - 4.75 %	
Carbon, C	<= 0.30 %	<= 0.30 %	
Copper, Cu	<= 0.25 %	<= 0.25 %	
Iron, Fe	<= 0.60 %	<= 0.60 %	
Manganese, Mn	<= 0.50 %	<= 0.50 %	
Nickel, Ni	>= 93 %	>= 93 %	Including Cobalt
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	
Titanium, Ti	0.25 - 1.0 %	0.25 - 1.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000424 ohm-cm	0.0000424 ohm-cm	Aged
Curie Temperature	15.0 - 50.0 Å°C	59.0 - 122 Å°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China