

Special Metals Electroformed Nickel, 200 Micron (8 mil) Foil, Electroformed and Annealed

Category : Metal , Nonferrous Metal , Nickel Alloy , Pure Element

Material Notes:

Data provided by the manufacturer, Special Metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Special-Metals-Electroformed-Nickel-200-Micron-8-mil-Foil-Electroformed-and-Annealed.php

Physical Properties	Metric	English	Comments
Density	8.91 g/cc	0.322 lb/in ³	
Thickness	203 microns	8.00 mil	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	102	102	200 g load
Tensile Strength, Ultimate	352 MPa	51000 psi	Transverse
	359 MPa	52000 psi	Longitudinal
Elongation at Break	28 %	28 %	Transverse
	39 %	39 %	Longitudinal

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.010 %	<= 0.010 %	
Chromium, Cr	<= 0.010 %	<= 0.010 %	
Cobalt, Co	<= 0.010 %	<= 0.010 %	
Copper, Cu	<= 0.010 %	<= 0.010 %	
Iron, Fe	<= 0.010 %	<= 0.010 %	
Nickel, Ni	>= 99.95 %	>= 99.95 %	
Sulfur, S	<= 0.0020 %	<= 0.0020 %	
Zinc, Zn	<= 0.0010 %	<= 0.0010 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000800 ohm-cm	0.00000800 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China