

Special Metals INCONEL® 706 Precipitation Hardening Alloy, Hot Finished Rod, 3 Part Heat Treatment, 0.562 inch (14.3 mm) Diameter

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy , Iron Base

Material Notes:

Tensile strength (ultimate and yield), shear strength, reduction of area, and elongation values reported here are typical for Hot Finished Rod, 3 Part Heat Treatment, 0.562 inch (14.3 mm) Diameter samples. Density and magnetic permeability are typical of precipitation hardened INCONEL® alloy 706. Other property values are typical of INCONEL® alloy 706. For optimum creep and rupture properties, the alloy receives a three part heat treatment as follows: Solution treat 1700-1850°F (925-1010°C) for a time commensurate with section size, then air cool. Stabilizing treatment 1550°F (845°C)/3 hr, air cool. Precipitation treatment 1325°F (720°C)/8 hr, furnace cool at 100°F (55°C)/hr to 1150°F (620°C)/8 hr, air cool. Data provided by the manufacturer, Special Metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Special-Metals-INCONEL-706-Precipitation-Hardening-Alloy-Hot-Finished-Rod-3-Part-Heat-Treatment-0562-inch-143-mm-Diameter.php

Physical Properties	Metric	English	Comments
Density	8.08 g/cc	0.292 lb/in ³	Precipitation Hardened

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1280 MPa	186000 psi	
Tensile Strength, Yield	993 MPa @Strain 0.200 %	144000 psi @Strain 0.200 %	
Elongation at Break	19 %	19 %	
Reduction of Area	28 %	28 %	
Modulus of Elasticity	210 GPa	30500 ksi	Dynamic Method
Poissons Ratio	0.382	0.382	Calculated by mfr.
Shear Modulus	76.0 GPa	11000 ksi	Dynamic Method
Shear Strength	876 MPa	127000 psi	Thickness not reported for this value

Thermal Properties	Metric	English	Comments
CTE, linear	13.46 Åµm/m-Å°C	7.478 Åµin/in-Å°F	Mean
	@Temperature 24.0 - 100 Å°C	@Temperature 75.2 - 212 Å°F	
	15.08 Åµm/m-Å°C	8.378 Åµin/in-Å°F	Mean
	@Temperature 24.0 - 300 Å°C	@Temperature 75.2 - 572 Å°F	

Thermal Properties	Metric	English	Comments
	@Temperature 24.0 - 500 °C	@Temperature 75.2 - 932 °F	Mean
	16.42 Åµm/m-Å°C	9.122 Åµin/in-Å°F	Mean
	@Temperature 21.0 - 700 Å°C	@Temperature 69.8 - 1290 Å°F	
Specific Heat Capacity	0.444 J/g-Å°C	0.106 BTU/lb-Å°F	
Thermal Conductivity	12.5 W/m-K	86.8 BTU-in/hr-ftÅ²-Å°F	
Melting Point	1334 - 1371 Å°C	2433 - 2500 Å°F	
Solidus	1334 Å°C	2433 Å°F	
Liquidus	1371 Å°C	2500 Å°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.060 %	<= 0.060 %	
Boron, B	<= 0.0060 %	<= 0.0060 %	
Carbon, C	<= 0.30 %	<= 0.30 %	
Chromium, Cr	14.5 - 17.5 %	14.5 - 17.5 %	
Cobalt, Co	<= 1.0 %	<= 1.0 %	
Copper, Cu	<= 0.35 %	<= 0.35 %	
Iron, Fe	38 %	38 %	As remainder
Manganese, Mn	<= 0.35 %	<= 0.35 %	
Nickel, Ni	39 - 44 %	39 - 44 %	Including Cobalt
Niobium, Nb (Columbium, Cb)	2.5 - 3.3 %	2.5 - 3.3 %	Includes Ta
Phosphorous, P	<= 0.020 %	<= 0.020 %	
Silicon, Si	<= 0.35 %	<= 0.35 %	
Sulfur, S	<= 0.015 %	<= 0.015 %	
Titanium, Ti	<= 0.40 %	<= 0.40 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000985 ohm-cm	0.0000985 ohm-cm	

Magnetic Permeability Electrical Properties	1.01 Metric	1.01 English	at 200 Oersted (15.9 kA/m); Annealed Comments
Curie Temperature	$\leq -78.0 \text{ }^{\circ}\text{C}$	$\leq -108 \text{ }^{\circ}\text{F}$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China