

## Star Plastics PC741 Molding Grade PC

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

### Material Notes:

Information provided by Star Plastics, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Star-Plastics-PC741-Molding-Grade-PC.php](http://www.lookpolymers.com/polymer_Star-Plastics-PC741-Molding-Grade-PC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	11 g/10 min @Load 1.20 kg, Temperature 300 Â°C	11 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.1 MPa	9000 psi	ASTM D638
Tensile Modulus	2.41 GPa	350 ksi	ASTM D638
Flexural Yield Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	73Â°F, 0.125 in.; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	129 Â°C	265 Â°F	unannealed, .125in; ASTM D648
Flammability, UL94	HB	HB	.045in
	V-2	V-2	.062in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	271 - 288 Â°C	520 - 550 Â°F	
Middle Barrel Temperature	277 - 299 Â°C	530 - 570 Â°F	
Front Barrel Temperature	288 - 316 Â°C	550 - 600 Â°F	
Nozzle Temperature	288 - 316 Â°C	550 - 600 Â°F	

<b>Processing Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Mold Temperature	76.7 - 104 °C	170 - 220 °F	
Drying Temperature	121 °C	250 °F	
Dry Time	4 hour	4 hour	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	
Screw Speed	40 - 75 rpm	40 - 75 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China