

Stellarchem GP-915UB TPE Compound

Category : Polymer , Thermoplastic , Elastomer, TPE , Olefinic TPE

Material Notes:

This grade of Stellarchem TPE is shear dependent and can be processed on conventional thermoplastics equipment for injection molding or extrusion. It's a soft, elastomeric polyolefin based, completely recyclable, colorable & non-hygroscopic thermoplastics elastomer material. Information provided by Stellarchem Polymer & Industrial

Order this product through the following link:

http://www.lookpolymers.com/polymer_Stellarchem-GP-915UB-TPE-Compound.php

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in ³	
Particle Mesh Size	80 - 150 Mesh	80 - 150 Mesh	
Melt Flow	8.16 g/10 min	8.16 g/10 min	JIS K7210

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	20	20	JIS K6301
Tensile Strength, Ultimate	5.10 MPa	740 psi	JIS K6301
Elongation at Break	1009 %	1009 %	JIS K6301
100% Modulus	0.00294 GPa	0.426 ksi	JIS K6301
300% Modulus	0.000294 GPa	0.0427 ksi	JIS K6301
Tear Strength	1.70 kN/m	9.69 pli	JIS K6301-B

Processing Properties	Metric	English	Comments
Processing Temperature	170 - 190 Â°C	338 - 374 Â°F	Metering Temperature, Extrusion
Rear Barrel Temperature	150 - 170 Â°C	302 - 338 Â°F	Injection Molding
	150 - 170 Â°C	302 - 338 Â°F	Extrusion
Middle Barrel Temperature	160 - 180 Â°C	320 - 356 Â°F	Injection Molding
	160 - 180 Â°C	320 - 356 Â°F	Transition, Extrusion
Front Barrel Temperature	170 - 190 Â°C	338 - 374 Â°F	Injection Molding
	180 - 200 Â°C	356 - 392 Â°F	Extrusion
Nozzle Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding

Die Temperature Processing Properties	180 - 200 Å°C Metric	356 - 392 Å°F English	Extrusion Comments
Melt Temperature	150 - 200 Å°C	302 - 392 Å°F	Injection Molding
	150 - 200 Å°C	302 - 392 Å°F	Extrusion
Mold Temperature	25.0 - 40.0 Å°C	77.0 - 104 Å°F	Injection Molding
Injection Pressure	5.00 - 40.0 MPa	725 - 5800 psi	Injection Molding
Back Pressure	0.500 - 1.00 MPa	72.5 - 145 psi	Injection Molding
Screw Speed	60 - 100 rpm	60 - 100 rpm	Extrusion
	100 - 200 rpm	100 - 200 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China