

Struktol TPW 609 Processing Additive

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer

Material Notes:

Blend of complex, modified fatty acid ester. Applications: STRUKTOL® TPW 609 has shown excellent results in producing extruded polymer / wood composites with or without coupling agents at a lower dosage than other lubricants on the market. STRUKTOL® TPW 609 offers very good mixing, improved filler dispersion and improved extrusion rates. Information provided by Struktol

Order this product through the following link:

http://www.lookpolymers.com/polymer_Struktol-TPW-609-Processing-Additive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 g/cc	1.00 g/cc	
Additive Loading	1.0 - 2.0 %	1.0 - 2.0 %	in PP/wood formulas
	3.0 - 4.0 %	3.0 - 4.0 %	In HDPE/wood applications

Thermal Properties	Metric	English	Comments
Dropping Point	114 - 154 Å°C	237 - 309 Å°F	

Processing Properties	Metric	English	Comments
Shelf Life	>= 24.0 Month	>= 24.0 Month	

Descriptive Properties	Value	Comments
Appearance	Beige pastille and powder	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China