

Styrolution Absolac® 300 ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Standard impact gradeHigh flowInformation provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Absolac-300-ABS.php

Physical Properties	Metric	English	Comments
Melt Flow	>= 30 g/10 min @Load 10.0 kg, Temperature 220 Â°C	>= 30 g/10 min @Load 22.0 lb, Temperature 428 Â°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	>= 20.0 kJ/mÂ²	>= 9.52 ft-lb/inÂ²	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	99.0 Â°C @Load 5.10 kg	210 Â°F @Load 11.2 lb	120Â°C/h; ASTM D 1525

Optical Properties	Metric	English	Comments
Gloss	98 %	98 %	Specular Gloss, 60Â°; ASTM D 523

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China