

Styrolution Absolac® 30GF15 ABS, 15% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled

Material Notes:

15% glass filled Information provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Absolac-30GF15-ABS-15-Glass-Filled.php

Physical Properties	Metric	English	Comments
Melt Flow	13 g/10 min @Load 10.0 kg, Temperature 220 °C	13 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	103 °C @Load 5.10 kg	217 °F @Load 11.2 lb	120 °C/h; ASTM D 1525

Optical Properties	Metric	English	Comments
Gloss	98 %	98 %	Specular Gloss, 60°; ASTM D 523

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China