

## Styrolution Absolac® 30GF30 ABS, 30% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Glass Fiber Filled

**Material Notes:**

30% glass filled Information provided by Styrolution

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Styrolution-Absolac-30GF30-ABS-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Styrolution-Absolac-30GF30-ABS-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Melt Flow	8.0 g/10 min @Load 10.0 kg, Temperature 220 Å°C	8.0 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched (ISO)	6.00 kJ/mÅ²	2.86 ft-lb/inÅ²	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	106 Å°C @Load 5.10 kg	223 Å°F @Load 11.2 lb	120Å°C/h; ASTM D 1525

Optical Properties	Metric	English	Comments
Gloss	98 %	98 %	Specular Gloss, 60Å°; ASTM D 523

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China