

Styrolution Absolan® 2300 Sparkle SAN

Category : Polymer , Thermoplastic , SAN Polymer

Material Notes:

Absolac 2300 Sparkle is a good flow grade Information provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Absolan-2300-Sparkle-SAN.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ISO 1183
Melt Flow	>= 45 g/10 min @Load 10.0 kg, Temperature 220 °C	>= 45 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	690 MPa	100000 psi	ISO 527

Thermal Properties	Metric	English	Comments
Vicat Softening Point	103 °C @Load 5.10 kg	217 °F @Load 11.2 lb	120 °C/h; ASTM D 1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China