

Styrolution Luran[®] S 778 UV Colored ASA

Category : Polymer , Thermoplastic , ASA Polymer

Material Notes:

Description: Injection molding grade with enhanced toughness and resistance to heat distortion. Especially suitable for exterior automotive components (e.g. radiator grills, rear end applique[®] panels and mirror housings). Information provided by STYROLUTION, which is a joint venture between BASF and INEOS

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Luran-S-778-UV-Colored-ASA.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ISO 1183
Water Absorption	1.65 %	1.65 %	Equilibrium; ISO 62
	0.45 %	0.45 %	ISO 62
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption at Equilibrium	0.35 %	0.35 %	23 [°] C/50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	5.35 g/10 min	5.35 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 [°] C	@Load 22.0 lb, Temperature 428 [°] F	

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	85.0 MPa	12300 psi	ISO 2039-1
	@Load 36.5 kg, Time 30.0 sec	@Load 80.5 lb, Time 0.00833 hour	
Tensile Strength, Yield	54.0 MPa	7830 psi	50 mm/min; ISO 527-1/-2
Elongation at Break	8.0 %	8.0 %	Nominal, 50 mm/min; ISO 527-1/-2
Elongation at Yield	3.4 %	3.4 %	50 mm/min; ISO 527-1/-2
Tensile Modulus	2.50 GPa	363 ksi	ISO 527-1/-2
Flexural Strength	80.0 MPa	11600 psi	ISO 178
Izod Impact, Notched	2.50 J/cm	4.68 ft-lb/in	ASTM D256
Charpy Impact Unnotched	9.00 J/cm ²	42.8 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 [°] C	@Temperature -22.0 [°] F	

Mechanical Properties	Metric	English	Comments
	25.0 J/cm ²	119 ft-lb/in ²	ISO 179/1eJ
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Tensile Creep Modulus, 1000 hours	1250 MPa	181000 psi	ISO 899-1
	@Strain <=0.500 %	@Strain <=0.500 %	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 - 110 Âµm/m-Â°C	44.4 - 61.1 Âµin/in-Â°F	ISO 11359-1/-2
	@Temperature 23.0 - 80.0 Â°C	@Temperature 73.4 - 176 Â°F	
Thermal Conductivity	0.170 W/m-K	1.18 BTU-in/hr-ft ² - Â°F	DIN 52612-1
Maximum Service Temperature, Air	90.0 Â°C	194 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	106 Â°C	223 Â°F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	103 Â°C	217 Â°F	ISO 75-1/-2
Vicat Softening Point	104 Â°C	219 Â°F	VST/B/50; ISO 306
	113 Â°C	235 Â°F	VST/A/50; ISO 306
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	IEC 60707
	@Diameter 4.00 mm	@Diameter 0.157 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	3.5	3.5	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Electrical Properties	Metric	English	Comments
	@Frequency 100 Hz	@Frequency 100 Hz	IEC 60250
Dielectric Strength	35.0 kV/mm	889 kV/in	K20/P20; IEC 60243-1
Dissipation Factor	0.0090	0.0090	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.033	0.033	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	600 V	600 V	Test Liquid A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 280 Å°C	464 - 536 Å°F	Injection
Mold Temperature	40.0 - 80.0 Å°C	104 - 176 Å°F	Injection
Drying Temperature	80.0 Å°C	176 Å°F	Pre-drying
Dry Time	2 - 4 hour	2 - 4 hour	Pre-drying

Descriptive Properties	Value	Comments
Color	Gray 35968	
	Gray 36565	
	Gray 36899	
	Gray 36934	
	Gray 37096	
	Natural	
	White 36508	
Commercial Status	Europe	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China