

## Styrolution Novodur® P2M-V ABS Pellets

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

### Material Notes:

Novodur® P2M-V has high impact strength, high gloss, and low emission. It is used for the production of molded plastic articles.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Styrolution-Novodur-P2M-V-ABS-Pellets.php](http://www.lookpolymers.com/polymer_Styrolution-Novodur-P2M-V-ABS-Pellets.php)

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	Test Condition: 60x60x2; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	Test Condition: 60x60x2; ISO 294-4
Melt Flow	18 g/10 min @Load 10.0 kg, Temperature 220 °C	18 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	100 MPa	14500 psi	ISO 2039-1
Tensile Strength, Yield	40.0 MPa	5800 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 15 %	>= 15 %	50 mm/min; acc. ISO 527-1,-2
Elongation at Yield	2.2 %	2.2 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min; ISO 527-1,-2
Flexural Strength	63.0 MPa	9140 psi	2 mm/min; ISO 178
Flexural Modulus	2.20 GPa	319 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	5.23 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 180-1A
	23.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	10.9 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 180-1A
Charpy Impact Unnotched	12.0 J/cm <sup>2</sup> @Temperature -30.0 °C	57.1 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179-1eU
	18.0 J/cm <sup>2</sup> @Temperature 23.0 °C	85.7 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1eU

Mechanical Properties <i>Charpy Impact, Notched</i>	Metric 1.10 J/cm <sup>2</sup>	English 8.23 ft-lb/in <sup>2</sup>	Comments ISO 179-1eA
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	2.20 J/cm <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	ISO 179-1eA
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	100 Âµm/m-Â°C	55.6 Âµin/in-Â°F	ISO 11359-1,-2; Parallel to Flow
	@Temperature 23.0 - 55.0 Â°C	@Temperature 73.4 - 131 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	98.0 Â°C	208 Â°F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	93.0 Â°C	199 Â°F	ISO 75-1,-2
Vicat Softening Point	97.0 Â°C	207 Â°F	50Â°C/hour; ISO 306
	@Load 5.10 kg	@Load 11.2 lb	
Flame Spread	55 mm/min	2.2 in/min	US-FMVSS; ISO 3795
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Glow Wire Test	700 Â°C	1290 Â°F	GWFI; IEC 60695-2-12
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	2.9	2.9	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.0	3.0	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	39.0 kV/mm	991 kV/in	IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.0050	0.0050	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0080	0.0080	IEC 60250

Electrical Properties	@Frequency 1.00e+6 Metric	@Frequency 1.00e+6 English	Comments
Comparative Tracking Index	600 V	600 V	Solution A, Rating; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	240 Â°C	464 Â°F	Injection Molding; ISO 294
Mold Temperature	70.0 Â°C	158 Â°F	Injection Molding; ISO 294
Injection Velocity	240 mm/sec	9.45 in/sec	Injection Molding; ISO 294

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China