

## Styrolution PS 1900 GPPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Extrusion Grade

### Material Notes:

Foam extrusion Very high flow High heat resistance Free of zinc and oil additives Information provided by Styrolution

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Styrolution-PS-1900-GPPS.php](http://www.lookpolymers.com/polymer_Styrolution-PS-1900-GPPS.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D 955
Melt Flow	23 g/10 min @Load 5.00 kg, Temperature 200 °C	23 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	74	74	ASTM D 785
Tensile Strength, Yield	34.5 MPa	5000 psi	ASTM D 638
Elongation at Break	1.0 %	1.0 %	ASTM D 638
Tensile Modulus	2.96 GPa	430 ksi	ASTM D 638
Flexural Strength	68.9 MPa	10000 psi	ASTM D 790
Flexural Modulus	3.31 GPa	480 ksi	ASTM D 790
Izod Impact, Notched	0.160 J/cm	0.300 ft-lb/in	ASTM D 638

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D 696
Vicat Softening Point	105 °C @Load 1.02 kg	221 °F @Load 2.25 lb	120°C/h; ASTM D 1525

Optical Properties	Metric	English	Comments
Refractive Index	1.59	1.59	Sodium D Line; ASTM D 542
Transmission, Visible	88 - 90 % @Wavelength 550 nm	88 - 90 % @Wavelength 550 nm	ASTM D 1003

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.5	2.5	ASTM D 150
	@Thickness 1.00 mm, Frequency 1.00e+6 Hz	@Thickness 0.0394 in, Frequency 1.00e+6 Hz	
Dielectric Strength	19.7 kV/mm	500 kV/in	ASTM D 696

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China