

## Styrolution PS 3600/3601 GPPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Molded, Unreinforced

### Material Notes:

Exceptional flow characteristics Good for thin wall and complex parts USP Class VI certified Information provided by Styrolution

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Styrolution-PS-36003601-GPPS.php](http://www.lookpolymers.com/polymer_Styrolution-PS-36003601-GPPS.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D 955
Melt Flow	14 g/10 min @Load 5.00 kg, Temperature 200 °C	14 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	74	74	ASTM D 785
Tensile Strength, Yield	42.7 MPa	6200 psi	ASTM D 638
Elongation at Break	2.0 %	2.0 %	ASTM D 638
Tensile Modulus	3.17 GPa	460 ksi	ASTM D 638
Flexural Strength	76.5 MPa	11100 psi	ASTM D 790
Flexural Modulus	3.31 GPa	480 ksi	ASTM D 790
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	ASTM D 638

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D 696
Vicat Softening Point	98.3 °C @Load 1.02 kg	209 °F @Load 2.25 lb	120°C/h; ASTM D 1525

Optical Properties	Metric	English	Comments
Refractive Index	1.59	1.59	Sodium D Line; ASTM D 542
Transmission, Visible	88 - 90 % @Wavelength 550 nm	88 - 90 % @Wavelength 550 nm	ASTM D 1003

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.5	2.5	ASTM D 150
	@Thickness 1.00 mm, Frequency 1.00e+6 Hz	@Thickness 0.0394 in, Frequency 1.00e+6 Hz	
Dielectric Strength	19.7 kV/mm	500 kV/in	ASTM D 696

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China