

Styrolution Terblend® N NM-19 ABS/PA6 (Conditioned)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS)/Nylon Blend , Nylon

Material Notes:

Terblend N NM-19 is a UV stabilized ABS/PA6 blend combining very high impact strength, even at low temperatures with an excellent processability and surface appearance. Information provided by STYROLUTION, which is a joint venture between BASF and INEOS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Terblend-N-NM-19-ABSPA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	dry; ISO 1183
Moisture Absorption at Equilibrium	1.4 %	1.4 %	beginning dry (23°C/50% R.H.); ISO 62
Melt Flow	19 g/10 min @Load 10.0 kg, Temperature 240 °C	19 g/10 min @Load 22.0 lb, Temperature 464 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	0.2 in/min; ASTM Test
Tensile Strength, Yield	32.0 MPa	4640 psi	2 in/min; ASTM Test
	34.0 MPa	4930 psi	50mm/min; ISO 527
Elongation at Break	50 %	50 %	50mm/min, Nominal strain; ISO 527
	>= 100 %	>= 100 %	0.2 in/min; ASTM Test
Elongation at Yield	5.5 %	5.5 %	50mm/min; ISO 527
Tensile Modulus	1.38 GPa	200 ksi	ASTM Test
	1.60 GPa	232 ksi	1mm/min; ISO 527
Izod Impact, Notched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM Test

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+11 ohm-cm	>= 1.00e+11 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+14 ohm	>= 1.00e+14 ohm	IEC 60093
Dielectric Constant	3.3 @Frequency 1.00e+6 Hz	3.3 @Frequency 1.00e+6 Hz	IEC 60250

Electrical Properties	Metric	English	Comments
Dissipation Factor	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Descriptive Properties	Value	Comments
Commercial Status	North America and Europe	
Primary Processing Technique	Injection Molding	
UL.UL-C	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China