

Styron DL 259NA Carboxylated SB

Category: Polymer, Thermoplastic, Styrene-Butadiene

Material Notes:

Performance Features: Ignition resistance, reduced water sensitivityApplications: Foil Laminated and Laminated (Metalized Paper)North

AmericaInformation provided by Styron

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-DL-259NA-Carboxylated-SB.php

Physical Properties	Metric	English	Comments
Solids Content	49 %	49 %	
pH	7.5	7.5	

Thermal Properties	Metric	English	Comments	
Glass Transition Temp, Tg	-6.00 °C	21.2 °F		

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China