## Styron Magnum<sup>™</sup> AG700 ABS, Low Gloss

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

## Material Notes:

MAGNUM® ABS resins are thermoplastic materials which provide an excellent balance of processability, impact resistance and heat resistance as imparted by the various polymer compositions. MAGNUM ABS resin are available in a wide range of melt flow rates, impact strength and heat resistance for both high and low gloss applications manufactured by injection molding, sheet or profile extrusion and thermoforming. The sheet and thermoforming grades of MAGNUM ABS resins provide excellent high and low gloss aesthetics, good thermal color stability, heat and impact resistance and stiffness for uses such as luggage, tool cases, burial vault liners, signs and recreation vehicle applications. Offering ranges in melt flow rates from 1.0 to 4.0, sheet Izod impacts from 130 to 560 J/m and sheet flexural modulus from 1960 to 2070 MPa, MAGNUM ABS resins can fill a variety of needs.MAGNUM AG700 ABS resin is the lowest gloss and highest melt flow rate option of the MAGNUM sheet grades. With a melt flow rate of 4.0 g/10 min., MAGNUM AG700 can be used for low gloss, low impact applications where easy processability is desired.Data provided by Dow Chemical.This product line was spun off from Dow Chemical to Styron in 2010.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Styron-Magnum-AG700-ABS-Low-Gloss.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM Data
Linear Mold Shrinkage	0.0055 cm/cm	0.0055 in/in	
Melt Flow	3.9 g/10 min	3.9 g/10 min	
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	ASTM Data

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	
Tensile Strength, Yield	30.3 MPa	4390 psi	ASTM Data
Elongation at Yield	1.8 %	1.8 %	ISO Data
Tensile Modulus	1.86 GPa	270 ksi	ASTM Data
Izod Impact, Notched	1.33 J/cm	2.49 ft-lb/in	ASTM Data
Charpy Impact Unnotched	NB	NB	ISO Data
	NB	NB	ISO Data, Low Temp
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in²	ISO Data, Low Temp
	1.60 J/cm <sup>2</sup>	7.61 ft-lb/in²	ISO Data



Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	74.0 μm/m-°C	41.1 µin/in-°F	ISO data
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	98.9 °C	210 °F	Annealed; ASTM Data
Vicat Softening Point	104 °C	219 °F	
Flammability, UL94	НВ	НВ	
	@Thickness 1.47 mm	@Thickness 0.0579 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China