

Styron Sprintan® SLR 4602 Solution Styrene Butadiene Rubber (S-SBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Composition: SPRINTAN® SLR-4602 Schkopau is manufactured by anionic solution polymerization using an organo-lithium initiator. The product has a medium styrene/high vinyl micro structure and a typical glass transition temperature of -25°C. SPRINTAN® SLR-4602 Schkopau is partially coupled and bears a GENERATION 2 functionalisation for improved polymer/filler interaction with carbon black as well as with silica. A non-staining stabiliser is added in the production. Application: SPRINTAN® SLR-4602 Schkopau provides outstanding wet grip/rolling resistance for fuel efficient tyre treads based on silica and/or carbon black. The high-vinyl micro structure makes SPRINTAN® SLR-4602 Schkopau applicable in summer-, all-season-, as well as in winter tyres. The material can also be used in high-quality technical rubber articles. Test Formulation (based on IRB7 black): Polymer - 100.0 parts by mass Stearic Acid - 1.50 parts by mass Zinc Oxide - 3.00 parts by mass Carbon Black IRB 7 - 50.0 parts by mass Aromatic Oil - 5.00 parts by mass Sulphur - 1.75 parts by mass Accelerator (CBS) - 1.00 parts by mass Information provided by Styron

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-Sprintan-SLR-4602-Solution-Styrene-Butadiene-Rubber-S-SBR.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	
Volatiles	0.30 % @Treatment Temp. 105 °C, Time 3600 sec	0.30 % @Treatment Temp. 221 °F, Time 1.00 hour	5 g in hot air oven; ASTM D5668
Mooney Viscosity	65 @Temperature 100 °C	65 @Temperature 212 °F	[MU] ML 1+4; ASTM D1646
Ash	0.050 %	0.050 %	ASTM D5667

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	63	63	ASTM D2240
Tensile Strength at Break	21.0 MPa @Treatment Temp. 145 °C, Time 2100 sec	3050 psi @Treatment Temp. 293 °F, Time 0.583 hour	Cure; ASTM D412
Elongation at Break	390 %	390 %	ASTM D412
300% Modulus	0.0152 GPa	2.20 ksi	ASTM D412
Rebound	26.4 %	26.4 %	Resilience; ISO 4662

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Glass Transition Temp, Tg Thermal Properties	-25.0 Å°C Metric	-13.0 Å°F English	HR 10 K/min, half height Comments
---	---------------------	----------------------	--------------------------------------

Chemical Properties	Metric	English	Comments
---------------------	--------	---------	----------

Styrene Content	21 %	21 %	Bound; ASTM D5775
-----------------	------	------	-------------------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Composition	0.63	Vinyl content
-------------	------	---------------

Rheometer	14.9 min	t _c (90), ASTM D5289
-----------	----------	---------------------------------

	19.5 dNm	MH, ASTM D5289
--	----------	----------------

	2.5 dNm	ML, ASTM D5289
--	---------	----------------

	6.4 min	t _s 2, test temperature 160Å°C; ASTM D5289
--	---------	---

	8.3 min	t _c (50), ASTM D5289
--	---------	---------------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China