

## Sumitomo Chemical ESPOLEX<sup>®</sup> 4675 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

ESPOLEX<sup>®</sup> TPE Series is a group of thermoplastic elastomers produced by Sumitomo Chemical Company. Among its material advantages, ESPOLEX<sup>®</sup> TPE Series is distinguished by offering many low-density grades that can provide substantial weight and cost savings over higher-density thermoplastic elastomers. In this regard, SUMITOMO CHEMICAL introduces specific gravity as a significant factor in reducing unit cost and weight. Products molded from ESPOLEX<sup>®</sup> TPE Series exhibit rubber-like properties that range from a soft elastic to a semi-hard rubber material. Like all thermoplastic elastomers, ESPOLEX<sup>®</sup> TPE Series offers substantial savings over thermoset rubber in manufacturing since it is processed using standard thermoplastic processing equipment and techniques, and it does not require the vulcanization required by conventional rubbers. Information provided by Sumitomo Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sumitomo-Chemical-ESPOLEX-4675-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Sumitomo-Chemical-ESPOLEX-4675-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in <sup>3</sup>	ASTM D792
Melt Flow	35 g/10 min @Load 10.00 kg	35 g/10 min @Load 22.05 lb	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	0 Sec Delay; ASTM D2240
Tensile Strength at Break	8.80 MPa	1280 psi	ASTM D412
Elongation at Break	830 %	830 %	ASTM D412
Compression Set	32 % @Temperature 23.0 °C	32 % @Temperature 73.4 °F	ASTM D395
	48 % @Temperature 70.0 °C	48 % @Temperature 158 °F	ASTM D395

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	170 - 220 °C	338 - 428 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China