

Supreme Petrochem SC 208 General Purpose Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Molded, Unreinforced

Material Notes:

Characteristics: High flow grade, Easy processing, Good clarity & shine. Processing: Extrusion Molding. Applications: Hand molding applications of novelty items, toys etc. Carrier for master batches, as a low profile additive in SMC and DMC applications. Also used for co-extrusion of glossy cap layer on sheets. Material Status: Commercial : Active. Agency Ratings: FDA 21 CFR 177.1640. Information provided by Supreme Petrochem LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Supreme-Petrochem-SC-208-General-Purpose-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	20 g/10 min @Load 5.00 kg, Temperature 200 Â°C	20 g/10 min @Load 11.0 lb, Temperature 392 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	43.1 MPa	6250 psi	50 mm/min; ASTM D638
Elongation at Break	2.0 %	2.0 %	50 mm/min; ASTM D638
Flexural Strength	71.6 MPa @Thickness 3.20 mm	10400 psi @Thickness 0.126 in	ASTM D790
Flexural Modulus	2.94 GPa @Thickness 3.20 mm	427 ksi @Thickness 0.126 in	ASTM D790
Izod Impact, Notched	0.180 J/cm @Thickness 3.20 mm	0.337 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	78.0 Â°C	172 Â°F	ASTM D648
Vicat Softening Point	96.0 Â°C	205 Â°F	1kg / 120Â°C; ASTM D1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 260 Â°C	356 - 500 Â°F	

Processing Properties

Metric 50.0 A°C

English 120 A°F

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China