

Supreme Petrochem SP6432 9690 Medium Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Characteristics High flow Good toughness Available in various colors Processing Injection molding Applications Air conditioner and cooler grills Refrigerator parts Washing machine components Material Status: Commercial : Active Agency Ratings: FDA 21 CFR 177.1640 Information provided by Supreme Petrochem LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Supreme-Petrochem-SP6432-9690-Medium-Impact-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	13.5 g/10 min @Load 5.00 kg, Temperature 200 Â°C	13.5 g/10 min @Load 11.0 lb, Temperature 392 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	27.0 MPa	3920 psi	50 mm/min; ASTM D638
Elongation at Break	35 %	35 %	50 mm/min; ASTM D638
Flexural Strength	44.1 MPa @Thickness 3.20 mm	6400 psi @Thickness 0.126 in	ASTM D790
Flexural Modulus	2.11 GPa @Thickness 3.20 mm	306 ksi @Thickness 0.126 in	ASTM D790
Izod Impact, Notched	0.700 J/cm @Thickness 3.20 mm	1.31 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	77.0 Â°C	171 Â°F	ASTM D648
Vicat Softening Point	96.0 Â°C	205 Â°F	1kg / 120Â°C; ASTM D1525
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 260 Â°C	356 - 500 Â°F	

Mold Temperature Processing Properties	40.0 - 60.0 A°C Metric	104 - 140 A°F English	Comments
---	---------------------------	--------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China