

Sylvin Technologies 8950-65 Natural PVC Extrusion Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Information provided by Sylvin Technologies Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sylvin-Technologies-8950-65-Natural-PVC-Extrusion-Compound.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.32 g/cc | 1.32 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|----------|------------|
| Hardness, Shore A | 65 | 65 | 10 seconds |
| Tensile Strength, Ultimate | 9.31 MPa | 1350 psi | |
| Elongation at Break | 435 % | 435 % | |
| Tear Strength Test | 190 | 190 | |

| Processing Properties | Metric | English | Comments |
|-----------------------|---------------|---------------|----------|
| Melt Temperature | 157 - 168 Â°C | 315 - 335 Â°F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China