

## Sylvin Technologies 9077-80 Natural PVC for Injection Molding

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Molded

**Material Notes:**

Information provided by Sylvin Technologies Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sylvin-Technologies-9077-80-Natural-PVC-for-Injection-Molding.php](http://www.lookpolymers.com/polymer_Sylvin-Technologies-9077-80-Natural-PVC-for-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	
Thickness	1000 microns	39.4 mil	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	10 seconds
Tensile Strength, Ultimate	9.31 MPa	1350 psi	
Elongation at Break	270 %	270 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	50.0 Å°C	122 Å°F	RTI
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	166 - 177 Å°C	330 - 350 Å°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China