TIMCAL TIMREX® 80X150 mesh FR Natural Flake Graphite

Category : Carbon , Graphite , Other Engineering Material , Additive/Filler for Polymer

Material Notes:

TIMREX Natural Flake Graphite is produced in a wide range of products distinguished by particle size distribution, chemistry and carbon content. Timcal mines the graphite from its own source in Lac-des-Îles, Quebec, Canada. Further processing can be done either in Lac-des-Îles or for high added value products (e.g. TIMREX PG25) in our new processing plant in Terrebonne, Quebec, Canada. All TIMREX"Naturals" are thoroughly controlled in our laboratories to ensure quality, consistency and total customer satisfaction.Advantages and applications: Suitable for all organic bonded friction materials, especially for linings in drum brakes as well as in brake pads for trains. Good transfer film formationGood thermal conductivityExcellent lubricating propertiesInformation provided by TIMCAL

Order this product through the following link:

http://www.lookpolymers.com/polymer_TIMCAL-TIMREX-80X150-mesh-FR-Natural-Flake-Graphite.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-------------|---------------|-------------------|
| Bulk Density | 0.740 g/cc | 0.0267 lb/in³ | Тар |
| Specific Surface Area | 0.90 m²/g | 0.90 m²/g | BET |
| Deformation | 1.2 % | 1.2 % | elastic |
| | 5.2 % | 5.2 % | plastic |
| | 6.4 % | 6.4 % | plastic + elastic |
| Ash | 4.0 - 6.0 % | 4.0 - 6.0 % | Guaranteed |
| | <= 7.0 % | <= 7.0 % | |

| Thermal Properties | Metric | English | Comments |
|----------------------|-----------|-----------------------|----------|
| Thermal Conductivity | 190 W/m-K | 1320 BTU-in/hr-ft²-°F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-----------|-----------|------------|
| Moisture Content | <= 0.50 % | <= 0.50 % | Guaranteed |
| | <= 0.50 % | <= 0.50 % | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|--------------------|
| Crystallite height Lc | >350 nm | |
| DBP absorption | 16 g/100g | (Dibutylphthalate) |

Contact Songhan Plastic Technology Co.,Ltd.



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China