

TIMET 6-6-2 Titanium Alloy (Ti-6Al-6V-2Sn), Solution Treated and Aged

Category : Metal , Nonferrous Metal , Titanium Alloy , Alpha/Beta Titanium Alloy

Material Notes:

Features: TIMETAL 6-6-2 offers improved strength properties and greater depth hardenability compared with TIMETAL 6-4. Data provided by TIMET.

Order this product through the following link:

http://www.lookpolymers.com/polymer_TIMET-6-6-2-Titanium-Alloy-Ti-6Al-6V-2Sn-Solution-Treated-and-Aged.php

Physical Properties	Metric	English	Comments
Density	4.53 g/cc	0.164 lb/in ³	Typical

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1205 MPa	174800 psi	Typical
Tensile Strength, Yield	1105 MPa @Strain 0.200 %	160300 psi @Strain 0.200 %	Typical
Elongation at Break	8.0 %	8.0 %	Typical
Modulus of Elasticity	115 GPa	16700 ksi	(Annealed)

Thermal Properties	Metric	English	Comments
Beta Transus	945 °C	1730 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	6.0 %	6.0 %	
Copper, Cu	0.50 %	0.50 %	
Iron, Fe	0.50 %	0.50 %	
Tin, Sn	2.0 %	2.0 %	
Titanium, Ti	85 %	85 %	Calculated as remainder
Vanadium, V	6.0 %	6.0 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China