

TIMET TIMETAL® 3-2.5 Titanium Alloy (Ti-3Al-2.5V; ASTM Grade 9) Aged

Category : Metal , Nonferrous Metal , Titanium Alloy , Alpha/Near Alpha Titanium Alloy

Material Notes:

Cold Workable Medium Strength Alloy. UTS, TYS, and elongation data below are specific to aged material; other specific condition entries are also available in MatWeb. Features: Cold formable and weldable, this alloy is used primarily for honeycomb foil and hydraulic tubing applications. Industrial applications such as pressure vessels and piping also utilize this alloy. Available with palladium stabilization to enhance corrosion resistance. The alloy is cold formable and easily welded, such like the commercially pure grades of titanium. Yet the alloys offer nearly double the strength over TIMETAL 50A. It is ASME Boiler and Pressure Vessel code approved. It offers the highest structural efficiency of any of the common engineering metals approved by ASME. The alloy is available in all common product forms including billet, bar, plate, sheet, strip, tubing and pipe. It is nonmagnetic. Typical heat treatment for this alloy: Stress Relief: 316-649°C for .5-3 hrs, air cool. Anneal: 649-760°C for 1-3 hrs, air cool. Solution treat: 871-927°C for .25-1 hrs, water quench. Aging: 482-538°C for 2-8 hrs, air cool. Data provided by TIMET.

Order this product through the following link:

http://www.lookpolymers.com/polymer_TIMET-TIMETAL-3-25-Titanium-Alloy-Ti-3Al-25V-ASTM-Grade-9-Aged.php

Physical Properties	Metric	English	Comments
Density	4.51 g/cc	0.163 lb/in ³	Typical

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	>= 828 MPa	>= 120000 psi	
Tensile Strength, Yield	>= 690 MPa	>= 100000 psi	
Elongation at Break	>= 8.0 %	>= 8.0 %	
Modulus of Elasticity	105 - 120 GPa	15200 - 17400 ksi	Typical
Poissons Ratio	0.30	0.30	
Shear Modulus	43.0 - 45.0 GPa	6240 - 6530 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	9.61 µm/m-°C	5.34 µin/in-°F	
	@Temperature 20.0 - 95.0 °C	@Temperature 68.0 - 203 °F	
Thermal Conductivity	8.30 W/m-K	57.6 BTU-in/hr-ft ² -°F	
	@Temperature 20.0 - 95.0 °C	@Temperature 68.0 - 203 °F	
Melting Point	<= 1700 °C	<= 3090 °F	
Liquidus	1700 °C	3090 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

Aluminum, Al	2.5 - 3.5 %	2.5 - 3.5 %	
Carbon, C	<= 0.080 %	<= 0.080 %	
Hydrogen, H	<= 0.015 %	<= 0.015 %	
Iron, Fe	<= 0.25 %	<= 0.25 %	
Nitrogen, N	<= 0.030 %	<= 0.030 %	
Oxygen, O	<= 0.15 %	<= 0.15 %	
Titanium, Ti	92.6 - 95.5 %	92.6 - 95.5 %	Calculated as remainder
Vanadium, V	2.0 - 3.0 %	2.0 - 3.0 %	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Resistivity	0.000127 ohm-cm	0.000127 ohm-cm	
------------------------	-----------------	-----------------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China