

## TIMET TIMETAL® 62S Titanium Alloy (Ti-6Al-2Fe-0.1Si); Beta Forged

Category : Metal , Nonferrous Metal , Titanium Alloy , Beta Titanium Alloy

### Material Notes:

Low Cost, Multipurpose Alloy. Tensile/toughness property data below for Beta Forged, RA material. Features: Properties and processing characteristics equivalent to or better than TIMETAL 6-4, but with significantly higher stiffness (elastic modulus). Due to the use of iron as the beta stabilizer, the alloy has lower formulation costs than TIMETAL 6-4. The combination of reasonable cost and excellent mechanical properties make TIMETAL 62S a practical substitute for many engineering materials. Typical heat treatment for this alloy: Mill Anneal at 760°C for 1-2 hrs, air cool Data provided by TIMET.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TIMET-TIMETAL-62S-Titanium-Alloy-Ti-6Al-2Fe-01Si-Beta-Forged.php](http://www.lookpolymers.com/polymer_TIMET-TIMETAL-62S-Titanium-Alloy-Ti-6Al-2Fe-01Si-Beta-Forged.php)

Physical Properties	Metric	English	Comments
Density	4.44 g/cc	0.160 lb/in <sup>3</sup>	Typical

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	986 MPa	143000 psi	Typical Longitudinal
	1000 MPa	145000 psi	Typical Transverse
Tensile Strength, Yield	945 MPa	137000 psi	Longitudinal, typical
	@Strain 0.200 %	@Strain 0.200 %	
	952 MPa	138000 psi	Transverse, typical
	@Strain 0.200 %	@Strain 0.200 %	
Elongation at Break	11 %	11 %	Typical Transverse in 2 in (50 mm)
	15 %	15 %	Typical Longitudinal in 2 in (50 mm)
Reduction of Area	16 %	16 %	Longitudinal
	20 %	20 %	Transverse
Modulus of Elasticity	128 GPa	18600 ksi	Typical
Fracture Toughness	64.0 MPa-m <sup>1/2</sup>	58.2 ksi-in <sup>1/2</sup>	K(IC); T-L Orientation
	67.0 MPa-m <sup>1/2</sup>	61.0 ksi-in <sup>1/2</sup>	K(IC); L-T Orientation
Bend Radius, Minimum	4.5 t	4.5 t	Typical; sheet
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Thermal Properties	Metric	English	Comments
	8.60 µm/m-°C	4.78 µin/in-°F	

CTE linear Thermal Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	Comments
	9.70 $\mu\text{m}/\text{m}\cdot\text{°C}$	5.39 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 250 °C	@Temperature 482 °F	
	10.6 $\mu\text{m}/\text{m}\cdot\text{°C}$	5.89 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 500 °C	@Temperature 932 °F	
Specific Heat Capacity	0.500 J/g-°C	0.120 BTU/lb-°F	
Thermal Conductivity	8.60 W/m-K	59.7 BTU-in/hr-ft <sup>2</sup> -°F	
Beta Transus	1024 °C	1875 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	5.5 - 6.5 %	5.5 - 6.5 %	
Carbon, C	<= 0.080 %	<= 0.080 %	
Hydrogen, H	<= 0.0125 %	<= 0.0125 %	
Iron, Fe	1.3 - 2.0 %	1.3 - 2.0 %	
Nitrogen, N	<= 0.040 %	<= 0.040 %	
Oxygen, O	0.15 - 0.20 %	0.15 - 0.20 %	
Silicon, Si	0.070 - 0.13 %	0.070 - 0.13 %	
Titanium, Ti	90.7 - 93 %	90.7 - 93 %	Calculated as remainder

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000163 ohm-cm	0.000163 ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China