TSE Industries EcoSPRAY® SS100 Aliphatic Polyurethane Resin

Category : Polymer , Thermoset , Polyurethane, TS

Material Notes:

TSE-EcoSPRAY® SS100 is an "Environmentally-Preferred Product" or EPP. It is an Aliphatic polyurethane resin free of Styrene, and is an "ultra-low" emitting resin during application. TSE-EcoSPRAY® SS100 is designed for the manufacturing of solid surfaces. This polyurethane is aliphatic. Therefore, solid surface technology manufactured using TSE-EcoSPRAY® SS100 exhibit excellent weather ability and good chemical resistance against weak acids and bases.All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-EcoSPRAY-SS100-Aliphatic-Polyurethane-Resin.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------------------|----------------------|----------|
| Specific Gravity | 1.08 g/cc | 1.08 g/cc | |
| | @Temperature 23.9 °C | @Temperature 75.0 °F | |
| Viscosity | 2000 cP | 2000 cP | |
| | @Temperature 23.9 °C | @Temperature 75.0 °F | |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|----------|-----------|---------------|
| Hardness, Barcol | 45 - 48 | 45 - 48 | clear casting |
| Tensile Strength, Yield | 70.3 MPa | 10200 psi | Clear Casting |
| Tensile Modulus | 2.67 GPa | 387 ksi | clear casting |
| Flexural Strength | 87.6 MPa | 12700 psi | clear casting |
| Flexural Modulus | 2.51 GPa | 364 ksi | clear casting |

| Thermal Properties | Metric | English | Comments |
|--|---------|---------|---------------------------------|
| Deflection Temperature at 0.46 MPa (66 psi) | 58.0 °C | 136 °F | clear casting; unspecified load |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------------------|----------------------|---|
| Gel Time | 40.0 - 60.0 min | 40.0 - 60.0 min | when reacted at 1:1.3 by weight, based on the application |
| | @Temperature 23.9 °C | @Temperature 75.0 °F | |
| Shelf Life | 6.00 Month | 6.00 Month | Sealed containers should be stored between 75°F and 95°F |
| | @Temperature 23.9 °C | @Temperature 75.0 °F | |

Contact Songhan Plastic Technology Co.,Ltd.



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China