

## TSE Industries Millathane® 5004 Millable Polyurethane Elastomer with 6 PHR Varox DBPH-50

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE 5004 is a millable polyurethane elastomer having excellent processing characteristics. MILLATHANE 5004 stocks can be readily processed on conventional rubber equipment. Vulcanization is carried out by the use of various peroxides including dicumyl peroxide (DCP) or 2,5-dimethyl-2,5-bis (t-butylperoxy) hexane (DBPH). Formulation Millathane 5004 100 Stearic Acid 0.25 Hi-Sil 23320 Varox DBPH-506 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-5004-Millable-Polyurethane-Elastomer-with-6-PHR-Varox-DBPH-50.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-5004-Millable-Polyurethane-Elastomer-with-6-PHR-Varox-DBPH-50.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	
Tensile Strength, Yield	22.1 MPa	3210 psi	
Elongation at Yield	380 %	380 %	
300% Modulus	0.0141 GPa	2.04 ksi	
Tear Strength	71.8 kN/m	410 pli	ASTM Die C

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 152 °C	@Temperature 305 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China