

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 0.5 PHR Zinc Stearate

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Zinc stearate has replaced cadmium stearate due to toxicity concerns with cadmium compounds. Used as a coactivator with Thanecure® ZM it shortens cure times and improves compression set. Zinc stearate also functions as a process aid and release agent, and helps prevent sticking to mill or internal mixer surfaces. All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-05-PHR-Zinc-Stearate.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-05-PHR-Zinc-Stearate.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	
Tensile Strength, Yield	33.0 MPa	4790 psi	
Elongation at Yield	565 %	565 %	
100% Modulus	0.00403 GPa	0.585 ksi	
200% Modulus	0.00958 GPa	1.39 ksi	
300% Modulus	0.0159 GPa	2.31 ksi	
Tear Strength	63.6 kN/m	363 pli	Die C
Compression Set	32.5 % @Temperature 70.0 °C, Time 79200 sec	32.5 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	8.00 min @Temperature 155 °C	0.133 hour @Temperature 311 °F	TC90

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China